TECHNICAL DATA SHEET



Name Code

61790 S1P SRC **ULTRA TOPOLINO S1P**

EN ISO Standard Weight **Product Range** Size range Mondopoint **Packaging** S1P SRC 10 pairs/carton 20345:2012 600 grams 35 <> 48 10,5 (1 shoe in size 42) (same size)

STROM >>

TECHNICAL SPECIFICATIONS





















SOLE

SOLE FEATURES









design, blending light, flexible PU foam midsoles with durable, grippy outsoles made of compact PU.

FORMULA

DUBLE

PROTECTIVE ELEMENTS





UPPER



LINING

TORSION

THERM RMED

FOOTBED



Measurement Unit

layer polyester, 40% lighter than steel, yet equally resistant up to 1,100 Newtons. It is non-magnetic, non-conductive, and provides superior thermal insulation insulating and hypoallergenic.

Test Result

The special wax applied to smooth full-grain leather creates a polished finish and a protective layer that enhances wear resistance and solidifies texture and color.

Three-layer wear-resistant lining featuring a microchannel network for unparalleled breathability and antimicrobial properties to prevent odors and microorganism growth.

Removable insole that distributes weight evenly, adapts to foot morphology and has anti-static, antibacterial, and antifungal properties. A cushioned heel insert adds comfort.



Requirement









SAFETY TECHNICAL SPECIFICATIONS

Description

2 confinen	mododromont ont	rioquii oiliolii	10011100011
TOE CAP: Impact resistance	mm	≥ 14	16,5
TOE CAP: Compression resistance	mm	≥ 14	16
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	pass
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	2,8
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	64
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	2,9
UPPER: Water vapour coefficient	mg/cm2	≥ 15	31
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	130,7
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	1045,8
OUTSOLE: Abrasion resistance	mm3	≤ 150	51
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	33
OUTSOLE: Flexural resistance	mm	≤ 4	1,3
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,3
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	1,7

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results
ΜΩ	-1.00	
	≤ 1,00	-
-	autsoles shall not melt and develop any cracks when bent	-
°C	≤ 10	-
°C	≤ 22	-
cm2	after 80 min.	-
МΩ	≤ 100	-
	°C cm2	- develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.

SOLE DESIGN AND PERFORMANCE



TRACTION STABILITY GRIP BRAKING SELF-CLEANING LADDER GRIP

ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT **75%**

INDUSTRIES



























STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

