TECHNICAL DATA SHEET



Name Code

99990 S3 FO SR **ORSETTO S3**

EN ISO Product Range Standard Weight **Packaging** Size range Mondopoint S3 F0 SR 10 pairs/carton 20345:2022 680 grams 35 <> 50 (1 shoe in size 42) (same size)



TECHNICAL SPECIFICATIONS



SOLE



























STEEL

Heat-treated and epoxy-coated safety

toe cap withstands impacts up to 200 Joules and compressions up to 15 kN.

Stainless steel fibers increase durability

and beveled edges enhance comfort









PROTECTIVE ELEMENTS





tecting the foot from penetration

by foreign objects.

a polyurethane film application makes this genuine leather com-

IDRO BARTON



LINING

THERM RMED

FOOTBED

pletely water-resistant, offering enhanced protection.

UPPER

Microfiber lining, treated to inhibit bacterial and microbial growth, boasts exceptional breathability and superior abrasion resistance

Removable insole that distributes weight evenly, adapts to foot morphology and has anti-static, antibacterial, and antifungal properties. A cushioned heel insert adds comfort.

EXTRA







SAFETY TECHNICAL SPECIFICATIONS

Description	Measurement Unit	Requirement	Test Result
TOE CAP: Impact resistance	mm	≥ 14	18,5
TOE CAP: Compression resistance	mm	≥ 14	18,5
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	1240
FOOTWEAR: Antistatic properties (in wet condition)	MΩ	≥ 0,1	6,6
FOOTWEAR: Antistatic properties (in dry condition)	$M\Omega$	≤ 1.000	155
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	2,3
UPPER: Water vapour coefficient	mg/cm2	≥ 15	25,2
UPPER: Water penetration after 60 min	g	≤ 0,2	0,2
UPPER: Water absorption after 60 min	%	≤ 30	18
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	28,6
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	229,4
OUTSOLE: Abrasion resistance	mm3	≤ 150	105
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	39
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	4,5
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	0,9

ADDITIONAL FEATURES

7.5577.517.12.71.27.12.5			
Measurement Unit	Requirement	Results	
mA	≤ 1,00	-	
-	autsoles shall not melt and develop any cracks when bent	-	
°C	≤ 10	-	
°C	≤ 22	-	
cm2	after 80 min.	-	
MΩ	≤ 100	-	
	mA - °C °C cm2	mA ≤ 1,00 - autsoles shall not melt and develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.	

SOLE DESIGN AND PERFORMANCE



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT 95%

INDUSTRIES



























STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

